IN THE CLAIMS:

- 1. (Currently amended) A light control film having a rough surface, wherein, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface, by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface $(\theta_{nv} \text{ (degree)})$ of the rough surface with respect to a base plane of the film is not less than 27 degrees and not more than 70 degrees at substantially any position on the light control film.
- 2. (Currently amended) A light control film having a rough surface formed by a patterned layer comprising a material having a refractive index n, wherein, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface, by using height data of the rough surface measured in with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface $(\theta_{nv} \text{ (degree)})$ of the rough surface with respect to a base plane of the film is not less than (59 20n) degrees and not more than 70 degrees at any position on the light control film.
- 3. (Currently amended) A light control film having a rough surface, wherein, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface, by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface (θ_{nv} (degree)) of the rough surface with respect to a base plane of the film and a ratio $A_r = A2/A1$ of an area A1 of the approximately square region-(A1) and a surface area A2 of the approximated curved surface of the rough surface (A2) ($A_r = A2/A1$) satisfy the following equation (1) or (2) at substantially any position on the light control film:

$$\theta_{nv} \div A_r \ge 22$$
 (1)
 $30 \le \theta_{nv} \times A_r \le 140$ (2).

4. (Currently amended) A light control film having a rough surface formed by a patterned layer comprising a material having a refractive index n, wherein, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface $(\theta_{nv} \text{ (degree}))$ of the rough surface with respect to a base plane of the film and a ratio A2/A1 of an area A1 of the approximately square region (A1) and a surface area A2 of the approximated curved surface of the rough surface $(A2) \text{ (A}_r = A2/A1)$ satisfy the following equation (3) or (4) at substantially any position on the light control film:

$$\theta_{nv} \div A_r \times n^2 \ge 35$$
 ... (3)
 $60 \le \theta_{nv} \times A_r \times n^2 \le 350$... (4).

5. (Currently amended) A light control film having a rough surface, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface (θ_{nv}) (degree) of the rough surface with respect to a base plane of the film is not less than 27 degrees and not more than 70 degrees, and an absolute value of a numerical value (A_{sk}) calculated in accordance with the equation (5) by using all the height data of the rough surface is not more than 1.2 is satisfied at substantially any position on the light control film:

$$A_{sk} = \frac{\sum_{i=1}^{m} z_i^3}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (5)$$

wherein, in fln the equation (5), z represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.}

6. (Currently amended) A light control film having a rough surface formed by a patterned layer comprising a material having a refractive index n, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface -(0_{nv} (degree)) of the rough surface with respect to a base plane of the film is not less than (59 - 20n) degrees and not more than 70 degrees, and an absolute value of a numerical value (Ask) calculated in accordance with the equation (5) by using all the height data of the rough surface is not more than 1.2 is satisfied at substantially any position on the light control film-|# 2|

$$A_{sk} = \frac{\sum_{i=1}^{m} z_i^3}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (5)$$

wherein, in fln the equation (5), z represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.}

7. (Currently amended) A light control film having a rough surface, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface (θ_{nv} (degree)) of the rough surface with respect to a base plane of the film is not less than 27 degrees and not more than 70 degrees, and a numerical value (A_{ku}) calculated in accordance with the equation (6) by using all the height data of the rough surface is not less than 1.5 and not more than 5.0 is satisfied at substantially any position on the light control film.

[# 3]

$$A_{ku} = \frac{\sum_{i=1}^{m} z_i^4}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (6)$$

[In the equation (6), z_i represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.]

[8]

8. (Currently amended) A light control film having a rough surface formed by a patterned layer comprising a material having a refractive index n, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, an average of slopes of the curved surface (θ_{nv}) (degree) of the rough surface with respect to a base plane of the film is not less than (59 - 20n) degrees and not more

than 70 degrees, and a numerical value $-(A_{ku})$ calculated in accordance with the equation (6) by using all the height data of the rough surface is not less than 1.5 and not more than 5.0 is satisfied at substantially any position on the light control film:

[#4]

$$A_{ku} = \frac{\sum_{i=1}^{m} z_i^4}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (6)$$

wherein, in the fln the equation (6), z_i represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.]

9. (Currently amended) A light control film having a rough surface, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, a ratio $A_r = A2/A1$ of an area A1 of the approximately square region A1 and a surface area A2 of the approximated curved surface of the rough surface A2 of a numerical value A3 calculated in accordance with the equation A3 by using all the height data of the rough surface is not more than 1.2 is satisfied at substantially any position on the light control film:

[#-5]

$$A_{sk} = \frac{\sum_{i=1}^{m} z_i^3}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (5)$$

wherein, in $\{Hn\}$ the equation- $\{5\}$, z_i represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.

10. (Currently amended) A light control film having a rough surface formed by a patterned layer comprising a material having a refractive index n, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, a ratio $A_r = A2/A1$ of an area A1 of the approximately square region A2 of the approximated curved surface of the rough surface A2 of the approximated curved surface of the rough surface A2 of a numerical value A3 calculated in accordance with the equation (5) by using all the height data of the rough surface is not more than 1.2 is satisfied at substantially any position on the light control film:

$$A_{sk} = \frac{\sum_{i=1}^{m} z_i^3}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (5)$$

wherein, in-f the equation f, f, f represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.

11. (Currently amended) A light control film having a rough surface, wherein a condition that, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger defined at an arbitrary position on the rough surface by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, a ratio $\underline{A}_r = \underline{A2/A1}$ of an area $\underline{A1}$ of the approximately square region- $\underline{(A1)}$ and a surface area $\underline{A2}$ of the approximated curved surface of the

rough surface (A2) ($A_r = A2/A1$) is not less than 1.2 and not more than 2.5, and a numerical value A_{ku} calculated in accordance with the equation (6) by using all the surface height data is not less than 1.5 and not more than 5.0 is satisfied at substantially any position on the light control film:

$$A_{ku} = \frac{\sum_{i=1}^{m} z_i^4}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_i^2}{m}} \cdots (6)$$

wherein, in {In the equation (6), z_i represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.}

12. (Currently amended) A light control film having a rough surface formed by a patterned layer comprising a material having a refractive index n, wherein, for a curved surface of the rough surface approximated in an approximately square region having an area of 1 mm² or larger, defined at an arbitrary position on the rough surface, by using height data of the rough surface measured at with predetermined intervals in for the longitudinal and transverse directions in the approximately square region, a ratio of an area of the approximately square region (A1) and a surface area of the approximated curved surface of the rough surface (A2) (A_r = A2/A1) is not less than (2 - 0.5n) and not more than 2.5, and a numerical value A_{ku} calculated in accordance with the equation (6) by using all the surface height data is not less than 1.5 and not more than 5.0 at substantially any position on the light control film:

$$A_{ku} = \frac{\sum_{i=1}^{m} z_{i}^{4}}{m} / \sqrt{\frac{\sum_{i=1}^{m} z_{i}^{2}}{m}} \cdots (6)$$

*

wherein, in {In the equation (6), z_i represents a value obtained by subtracting a height of average plane of the rough surface from a measured surface height, and m represents a number of measurement points.}

- 13. (Currently amended) The light control film according to claim 1, wherein absolute value of average- (ϕ_{ave}) of angles, wherein - $(\phi$ satisfies the inequality τ -180 degrees < ϕ 180 degrees, between orthogonal projections of normals of the curved surface of the rough surface projected on the base plane and one side of the approximately square region, is not more than 5 degrees irrespective of the direction along which the approximately square region is defined in the rough surface.
- 14. (Previously presented) A backlight unit comprising a light guide plate equipped with a light source on at least one end portion thereof and having a light emergent surface approximately perpendicular to the end portion and a light control film provided on the light emergent surface of the light guide plate, wherein the light control film according to claim 1 is used as the light control film.
- 15. (Original) The backlight unit according to claim 14, wherein a prism sheet is used between the light control film and the light guide plate.
- 16. (Previously presented) A backlight unit comprising a light source, a light diffusive plate provided on one side of the light source and a light control film provided on the side of the light diffusive plate opposite to the light source side, wherein the light control film according to claim 1 is used as the light control film.